

Halogen-free/Low-smoke/Flame-retardant Non-woven Tapes MFRWD

Composition: Polyester fiber, adhesive, non-halogen flame retardant powder

Application:

Applications for fire retardant layers of pollution-free fire retardant cables and fire resistant cables.

		Types	
Property	Unit	MFRWD-20	Test Method
Mass per unit area	g/m ²	250±30	ISO9073-1
Thickness	mm	0.20±0.05	ISO9073-2
Tensile Strength	N/cm	≥60	ISO9073-3
Elongation	%	≥10	ISO9073-3
Oxygen index	%	≥35	GB5454-1997
Smoke density	°C	≤100	ASTM E 662-1983
Gas emission in burning	PH value	≥4	IEC 60754-2-1991
	us/mm conductivity	≤4	IEC 60754-2-1991

Spool is ordered from 150mm-700mm. Width, ID available on request.
Other specifications available on request.